



# KüraGuard Precision Protection



RCS Healthcare

RCS Healthcare is a market leader in PPE, dedicated to providing the highest quality of protective equipment and care.

KüraGuard nitrile examination gloves have been designed for a hygienic, easy fit in a range of sizes. Easily identified by their purple color, KüraGuard latex-free examination gloves provide protection and comfort in medical environments.



Examination  
Gloves

3.2g

## FEATURES:

- Latex-free formulation
- Powder-free to reduce skin sensitivity
- Beaded cuff to reduce rips
- Compliant with ASTM standards
- Easy dispensing carton

<b>Type</b>	Nitrile Examination Glove - Disposable
<b>Material</b>	Nitrile Butadiene Rubber (NBR)
<b>Color</b>	Purple
<b>Design &amp; Feature</b>	Ambidextrous, Beaded Cuff, Finger Textured
<b>Donning Aid</b>	Chlorinated
<b>Product Classification</b>	FDA 88O.625O MOD: Class I
<b>Powder Content</b>	Less than 2.0 milligram/glove
<b>Protein Content</b>	N/A
<b>Size Available</b>	S, M, L, XL
<b>Storage Condition</b>	Product should be stored in a dry, ventilated room, avoiding direct sunlight.
<b>Shelf Live</b>	Product has a shelf life of 3 years from the date of manufacture, if stored correctly.
<b>Packing Style</b>	100 pcs in one inner dispenser box. Each carton holds 10 boxes.
<b>Performance Standard</b>	ASTM D6319 ASTM D5151 ASTM D412 ASTM D573 ISO 9001 ISO 13485



PHYSICAL DIMENSION - 3.2g, 240 MM/G"					
Size	XS	S	M	L	XL
Ave width (mm)	75 ± 5	85 ± 5	95 ± 5	105 ± 5	115 ± 5
Ave weight (gm)	2.6 ± 0.2	2.9 ± 0.2	3.2 ± 0.2	3.5 ± 0.2	3.8 ± 0.2
Length(mm)	Min. 240				
Thickness	Cuff	0.04			
	Palm	0.05			
	Finger	0.07			

PHYSICAL PROPERTIES - ASTM						
Parameters	Before Aging			After Aging		
	Tensile Strength (MPa)	Elongation at break(%)	Modulus at 500% (MPa)	Tensile Strength (MPa)	Elongation at break (%)	Modulus at 500% (MPa)
ASTM Requirement	Min 14	Min 500%	Min 2.8	Min 14	Min 400%	Min 2.8

CHEMICAL ANALYSIS		
Parameters	Protein Content	Powder Content
		N/A
ASTM Requirement	N/A	Max 2.0 milligram/glove

PERFORMANCE			
Inspection	Related Defects	Inspection level	AQL
Watertight Test	Barrier	G-1	1.5
Visual Inspection	Major Defects		2.5
	Minor Defects		4.0
Physical Properties	Tensile Strength and Elongation	S-2	4.0
Physical Dimensions	Measurement	S-2	4.0



**KuraGuard**  
Precision Protection

703 PIER AVE, SUITE 375, HERMOSA BEACH, CA 90254  
PHONE: 888.404.1911 | WWW.RCSHCG.COM